

PRODUCT INFORMATION

SEPLITE Monojet™ SC3100

Uniform particle size, Gel Strong acid cation resin for Industrial softening and demineralization applications



·Descriptions

SEPLITE® Monojet™ SC3100 Ion Exchange Resin is suitable for using in industrial softening and demineralization applications especially for high performance and cost-effective requirements. Thanks to the uniform particle size and excellent chemical properties, this resin is able to yield high operating capacity and help users to save the chemical regenerant and rinsing water.

SEPLITE® Monojet™ SC3100 is compatible with co-current or counter-current systems as well as mixed bed or single bed. The resin could be available in Na+ or H+ form.

The resins are produced fully in accordance with the FDA (US Food & Drug Administration), also meeting the regulations prescribed under Resolution ResAP (2004) 3 on ion exchange and adsorbent resins used in the processing of foodstuffs.

Please follow our start-up recommendations which is available upon request, when using our products in food applications.

·Physical and Chemical Characteristics

Matrix Structure	Gel, Styrene-divinylbenzene	
Functional group	Sulfonic acid	
Shipping form	Na+ (H+ is also available)	
Physical Appearance	Amber to dark brown translucent spherical beads	
Particle size (mm)	0.60 ± 0.05 mm <0.3mm ≤0.1% ≥0.85mm ≤3.0%	
Moisture content (%)	42-48(Na+Form)	50-55(H+Form)
Total Capacity(eq/L)	≥2.0(Na+Form)	≥1.8(H+Form)
Bulk Density (g/l)	750-850	720-820
Density (g/l)	1260-1300	1170-1220
Whole beads count (%)	≥95	≥95
Uniformity coefficient	≤1.1	≤1.1

·Applications

- ☐ Industrial softening
- ☐ Industrial Demineralization

PRODUCT INFORMATION

SEPLITE Monojet™ SC3100

Uniform particle size, Gel Strong acid cation resin for Industrial softening and demineralization applications



Recommended Operating Conditions

Operating temp.	max. °C	120 0-14 800 280
Operating pH		15-25 (at 20°C) 4
Min. Bed depth	mm	(at 20°C, per m/h)
Pressure drop	max. kPa	60-100 HCl / H ₂ SO ₄
Backwash flow rate	max. m/h	/ NaCl
Backwash Bed expansion	Approx. vol.%	50 / 80/ 60
Backwash Freeboard	vol. %	4-6 / 1.5-3 / 8-10
Regenerant (counter-current regeneration)		15-20
Regeneration level		
Regeneration concentration	Approx. g/l	5 / 10-20
Contact time	wt.%	2-5
Regeneration flow rate	Minutes	HCl / H ₂ SO ₄ / NaCl
Rinse water requirement(slow/fast)	Approx. m/h	100 / 150 / 120
Regenerant (co-current regeneration)	Approx. BV	6-10 / 1.5-3 / 8-10
Regeneration level		30-40
Regeneration concentration	Approx. g/l	5
Contact time	wt.%	4-7
Regeneration flow rate	Minutes	
Rinse water requirement(slow/fast)	Approx. m/h	
	Approx. BV	

Hydraulic Characteristics

Typical values of pressure drop across a bed of SEPLITE® Monojet™ SC3100 are given for a range of operating flow rate in Fig. 1.

Fig. 2 shows the Bed expansion which is a function of flow rate and temperature. Be cautious to avoid loss by accidental over-expansion of the bed.

Fig. 1 Pressure Drop





Fig. 2 Backwash Expansion



PRODUCT INFORMATION

SEPLITE Monojet™ SC3100

Uniform particle size, Gel Strong acid cation resin for Industrial softening and demineralization applications



·Precautions

Resins should be stored in sealed containers or bags where temperature was above 0°C in dry conditions without exposure to direct sunlight.

Do not mix ion exchange resin with strong oxidizing agents; otherwise it will cause violent reactions.

In case of eyes contact with resins, rinse eyes immediately with plenty of water, and consult a specialist.

Material and samples must be disposed according to local regulations.

Dry polymers will expand when become wetted and may cause an exothermic reaction.

Spilled materials may be slippery.

SEPLITE® and Monojet™ are registered trademarks of Sunresin New Materials Co. Ltd., Xi'an

·This information is general information and may differ from that based on actual conditions. For more information about SEPLITE resins, please contact SUNRESIN® directly.

All information set forth herein is for informational purposes only. This information is general descriptive(introductory) information of SUNRESIN and its related products, technologies and services. Neither shall constitute the guarantee of SUNRESIN and its affiliates to products, technologies and services in specific fields and specific application conditions results, unless otherwise expressly noted. SUNRESIN and its affiliates assumes no obligation or liability for the information in this document. Customer is responsible for judging whether the information is appropriate for Customer's concrete demand and are obliged to understand whether the use of these products, technologies and services is permitted by the laws and regulations of their countries and relevant regions. Unless expressly stated, no freedom from infringement of use any patent or trademark or intellectual property rights owned by SUNRESIN or its affiliated companies under this document is to be inferred.